



Aalborg Universitet

AALBORG UNIVERSITY
DENMARK

The influence of ferric ion impurities on a proton exchange membrane electrolyzer operated at varying temperature and current density conditions

Li, Na; Simon Araya, Samuel; Kær, Søren Knudsen

Publication date:
2019

[Link to publication from Aalborg University](#)

Citation for published version (APA):

Li, N., Simon Araya, S., & Kær, S. K. (2019). *The influence of ferric ion impurities on a proton exchange membrane electrolyzer operated at varying temperature and current density conditions*. Poster presented at 2nd International Conference on Electrolysis 2019, Loen, Norway.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal -

Take down policy

If you believe that this document breaches copyright please contact us at vbn@aub.aau.dk providing details, and we will remove access to the work immediately and investigate your claim.

Introduction

A water purification system is typically used in PEM water electrolysis systems, but over time the quality of the circulating water may deteriorate due to metallic impurities originating from the piping system, catalyst layers and other components degradation. These impurities lead to a progressive increase of the cell voltage [1].

In this work, the influence of 5 ppm Fe^{3+} contamination on cell performance of PEM water electrolysis has been investigated, and the temperature and current density effects on cell performance in the presence of Fe^{3+} were also studied.

Experimental setup




Fig. 1: Schematic of the experimental setup

Results and discussion

The Electrochemical impedance spectroscopy (EIS) and polarization results showed that cell performance decreased severely when 5 ppm of Fe^{3+} solution in water was tested in an electrolyzer cell.




Fig. 2: voltage profile of the entire test period

In Fig. 2, where the voltage profile of the entire test period is given, it can be seen that the voltage of the cell increases significantly compared to DI water operation, after introducing Fe^{3+} ions from the 4th hour of the testing on-wards. Consequently, the The IV curve slopes became significantly steeper after Fe^{3+} ions are introduced, showing the increase in the overall resistance, as can be seen in Fig. 3.




Fig. 3: polarization curves at different test conditions

As shown in Fig. 4 for DI water operation, both high temperature and low current density can improve the cell performance, where the ohmic resistance decreased clearly.

In the case of contaminated feed solution, the cell performance decreases progressively, even at higher temperature and lower current density, as can be seen in Fig. 5.




Fig. 4: EIS spectra at different operating conditions with DI water feed

Higher temperature (80 °C) reduces the ohmic resistance, both for DI water and contaminated solution operation. Whereas, higher current density (2 A/cm²) seems detrimental at lower temperatures in the presence of Fe^{3+} ions, but can contribute to reduced mass transfer resistance at higher temperature.




Fig. 5: EIS spectra at different operating conditions with contaminated solution

A strong effect of ionic contamination is seen throughout the tested frequency spectrum. This can be explained by the higher affinity of Fe^{3+} ions than protons for the sulfonic acid group sites, which could substitute protons in normal ion exchange processes [2] and by membrane degradation through radical attack promoted by the metallic ions [3].

Conclusions

It has been shown that the cell performance degrades severely with Fe^{3+} in feed water. The Fe^{3+} ions adsorbed on Nafion membrane and catalyst layers, resulting in the increase of membrane ohmic resistance and charge transfer resistance on both electrodes. Furthermore, some metallic impurities may promote the generation of hydroxide radicals from hydrogen peroxide and hence degrade the membrane severely by the caused Fenton mechanism [3, 4]. High temperature operation can contribute to improve cell performance at the tested Fe^{3+} concentration.

References

- [1] Shucheng Sun, Zhigang Shao, Hongmei Yu, Guangfu Li, and Baolian Yi. Investigations on degradation of the long-term proton exchange membrane water electrolysis stack. *Journal of Power Sources*, 267:515–520, dec 2014.
- [2] Michael J. Kelly, Günter Fafilek, Jürgen O. Besenhard, Hermann Kronberger, and Gerhard E. Nauer. Contaminant absorption and conductivity in polymer electrolyte membranes. *Journal of Power Sources*, 145(2):249–252, aug 2005.
- [3] Christoph Rakousky, Uwe Reimer, Klaus Wippermann, Marcelo Carmo, Wiebke Lueke, and Detlef Stolten. An analysis of degradation phenomena in polymer electrolyte membrane water electrolysis. *Journal of Power Sources*, 326:120–128, sep 2016.
- [4] Na Li, Samuel Simon Araya, and Søren Knudsen Kær. The effect of Fe^{3+} contamination in feed water on proton exchange membrane electrolyzer performance. *International Journal of Hydrogen Energy*, apr 2019.

Acknowledgement

The authors would like to acknowledge the financial support from Innovation Fund Denmark through the e-STORE project, Grant No. 4106-00025B. Na Li appreciates China Scholarship Council for the financial support.